

15<sup>th</sup> March 2012

Flameproofings Ltd  
Units 1 & 2  
Lyon Industrial Estate  
Kearsley  
Bolton  
BL4 8NB

FAO: John Brannan

### Martindale abrasion test

Fabric: A) Juno

The fabrics were subjected to an indicative test with 150,000 rub cycles to the upholstery test BS EN ISO 12947-2: 1999 Part 2 "Determination of Specimen Breakdown", with a 12KPa load ( $795 \pm 7$ gms) by the Martindale method.

In this case the pile had been partially removed but there was no thread breakage on the base fabric.

It is the opinion of our laboratory that both fabrics showed a satisfactory result.

Peter Collings  
Technical Manager



As Supplied



150,000 rubs

#### **THOR SPECIALITIES (UK) LIMITED**

Wincham Avenue · Wincham · Northwich · Cheshire CW9 6GB · ENGLAND

Telephone: +44 (0)1606 818800 · Telefax: +44 (0)1606 818801

Email: [info@thor.uk.com](mailto:info@thor.uk.com) · [www.thor.com](http://www.thor.com)



Directors: D A Hewitt · K J Seal

Registered in England No: 1761700 · Registered address as above