

Our Ref: SW/MG/BR

02 August 2013

Report 205552

Page 1 of 3

Agua Fabrics Limited
Hyde House
The Hyde
London
NW9 6LH

Contact: Robert

DATE RECEIVED	:	26 JULY 2013
QUALITY/REFERENCE	:	VISTAS
REPUTED FIBRE CONTENT	:	65% PVC, 32% COTTON/PES, 2% PU
COLOUR/DESIGN	:	BLACK
FABRIC DESCRIPTION	:	COATED
END USE	:	UPHOLSTERY
PERFORMANCE STANDARD	:	BS2543:2004

Based on lowest classification of the results obtained for the tests carried out, the fabric submitted would meet the requirements for General Domestic (GD) Use.

Tests	Method	Level (BSEN 14465)	Classification (BS2543)
Colour fastness to rubbing	BS EN ISO 105-X12:2002	A	All grades
Colour fastness to light	BS EN ISO 105-B02:1999	B	GC
Seam Slippage	BS EN ISO 13939-2:2004	A	All grades
Tensile strength	BS EN ISO 13934-1:1999	A	All grades
Tear strength	BS EN ISO 13937-3:2000	B	All grades
Resistance to abrasion	BS EN 14465:2003 Annex A	A	All grades

Note: GD = General domestic; GC = General Contract



S. WISEMAN
LABORATORY MANAGER



M. GRAINGER
SENIOR TECHNOLOGIST

This report shall not be reproduced except in full without the written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.

Our Ref: SW/MG/BR

02 August 2013

Report 205552

Page 2 of 3

COLOUR FASTNESS TO:

BS EN ISO 105-X12:2002 RUBBING

Colour	Test	Staining	Requirement
	Dry, Face, Length	4-5	4 min
	Dry, Face, Width	4-5	
	Wet, Face, Length	4-5	
	Wet, Face, Width	4-5	

BS EN ISO 105-B02:1999 LIGHT

Shade change	
	5+

PHYSICAL

BS EN ISO 13936-2:2004 SEAM SLIPPAGE

	Length	Width
Seam opening at 180 Newtons	3.3 mm	3.7 mm

BS EN ISO 13934-1:1999 TENSILE STRENGTH 50mm strip

Length	Width
671.0N	738.7 N

BS EN ISO 13937-3:2000 WING TEAR STRENGTH

Length	Width
37.6 N	46.3 N

Our Ref: SW/MG/BR

02 August 2013

Report 205552

Page 3 of 3

BS EN ISO 12947:1998 ABRASION - END POINT

12 kPa Load

	Cycles
Head 1	50,000+
Head 2	50,000+
Head 3	50,000+
Head 4	50,000+
Shade change	4-5

Note: The overall performance level is based on the lowest result obtained.