

Lancashire Testing Services Ltd
 Units 26 & 27
 Lyon Road Industrial Estate
 Kearsley
 BOLTON
 BL4 8NB



Test Report

Lab Ref number:	LTS1700070-2
Date:	24/04/2017
Sample submitted:	Fusion
Customer	Agua Fabrics Ltd
Colour:	Parchment
Substrate:	PVC
Filling used:	Carpenter/RX36110 unmodified polyurethane foam of density 33Kg/m ³ /Type B, 130
Test Required:	IMO 2010 FTP Code Part 8
Pre Treatment:	Non Required

Testing source			Smouldering Cigarette source					
Testing time limit			60 minutes after placement of smouldering cigarette					
Test No.	Position	Ignition/ Non Ignition	Duration of: (min.sec)			Time for: (min.sec)		
			Ignition source	Flames	Smoke	Ignition of Test pieces	Cover Splitting	Extinction
1	RHS	NI	10.22	-	12.04	-	-	-
2	M	NI	14.01	-	16.22	-	-	-

Testing source			Butane Flame Ignition Source 1					
Testing time limit			2 minutes after removal of burner tube					
Test No.	Position	Ignition/ Non Ignition	Duration of: (min.sec)			Time for: (min.sec)		
			Ignition source	Flames	Smoke	Ignition of Test pieces	Cover Splitting	Extinction
1	M	NI	20	22	35	-	-	-
2	LHS	NI	20	23	33	-	-	-

RESULT:	SMOULDERING CIGARETTE SOURCE	Non Ignition
	BUTANE FLAME IGNITION SOURCE 1	Non Ignition
KEY: I = Ignition, NI = Non Ignition, LHS = Left hand side, M = Middle, RHS = Right hand side		

The results detailed relate only to the sample submitted and offer no guarantee for the batch or bulk of material produced. Please be advised that these results are only intended for advisory purposes as full test procedures may not have been used in their entirety.